

Thermoplastic Elastomer TPE

General notes:

- » TPE Olefinic Thermoplastic Elastomer, Permanent Antistatic
- » Soft Plastic, was developed in order to achieve a surface resistance 10⁸-10⁹ Ohm in order to minimize the possibility of charge generation by wearing
- » ESD Protection



Mechanical properties

Tensile strength	2 MPa	ISO 527 ASTM D 638
Tensile elongation	10 +%	ISO 527 ASTM D 638
Hardness, Shore	65-75 A	D-785

Polypropylen compound PP

General notes:

- » PP polypropylene-compound
- Hard Plastic, its function is to ground the metal tool (through the operators hand and the ESD wrist strap)
- » ESD Protection





Soft plastic (TPE)

Upper side

Mechanical properties

Tensile strength at break (5mm/min) Elongation at break (5mm/min) Tensile modulus +23°C Tensile strength +23°C Izod-Impact strength (notched) +23°C	20 MPa >10% 1650 MPa 190 MPa 13 kJ/m	ISO 527 ASTM D 638 ISO 527 ASTM D 638 ISO 527 ASTM D 638 ISO 527 ASTM D 638 ISO 179/2C
Thermal properties		
Temp. of defl. under load (1.80 MPa) VICAT softening point B (49 N)	56 °C 70 °C	ISO 75 ASTM D 648 ISO 306
Other properties		
Density	0.97 g/cm³	ISO 1183

This document contains information based on average values as obtained from the results of laboratory tests and observations made on the material. Ideal-tek SA declines all responsibility from an improper use of the product described in this document.